

DICCO LASYR

DESCRIPTION

A solvent borne transparent stain.

EMISSION CLASSIFICATION

The stain does not contain free formaldehyde and after drying it does not emit formaldehyde to the environment.

PRODUCT FEATURES AND RECOMMENDED USES

- ◆ A semi-opaque stain.
- ◆ Recommended for furniture, doors of kitchen fittings and other wooden surfaces indoors.

TECHNICAL DATA

Solids content about 10 - 15 weight %.

Specific gravity 0.85 - 0.95 kg/litre.

Product code 313 serie

Theoretical coverage 0.5 m²/l (100 µm).
Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Application details

Application technique	Viscosity DIN4
Low pressure spraying	Delivery viscosity
Airless spraying	Delivery viscosity

Drying times (40 - 100 g/m²)

	20 °C	50 °C
Recoatable, after	30 min	10 min

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Thinner Thinner 1033 or 1027.

Cleaning of equipment Thinner 1033 or 1027.

Colours TEMASPEED tinting. The shade of the product may vary according to the used wood material.

DICCO LASYR

APPLICATION DETAILS

Application	<p>Stir the stain very carefully before use. Stir also after breaks during working day before continuing the work. The stain is ready for use.</p> <p>Different application methods and sorts of wood may cause variations of the colour of the stain. The colour and intensity of the stain should be verified before applying.</p>
Application conditions	<p>The surface to be treated has to be clean and dry. During application and drying the temperature of the air, the surface to be treated and the stain has to be over 18 °C and the relative humidity of the air below 70 %.</p>
VOC	<p>The Volatile Organic Compounds amount is 800 g/litre of paint. Maximum VOC content in ready to use paint (thinned 10 % by volume) is 800 g/l.</p>
HEALTH AND SAFETY	<p>Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oy.</p>

rer150606/snl030108/313-s.