

PINJASOL COLOR

DESCRIPTION

A transparent priming oil.

PRODUCT FEATURES AND RECOMMENDED USES

- ◆ Contains effective anti-rot and anti-mould agents.
- ◆ Suitable for wooden surfaces such as window frames, front doors, wall boards, log cabins etc.

TECHNICAL DATA

Solids content abt. 11 % by volume, 14 % by weight.

Specific gravity 0.82 kg/l (clear).

Product code 292 series

Theoretical coverage 8 - 10 m²/l (100 µm).
Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Storage (23 °C) 6 months.

Application details

Application technique	Viscosity DIN4
Dip coating	Delivery viscosity
Spraying	Delivery viscosity
Brushing	Delivery viscosity

Drying times (110 - 120 g/m²)

	+ 20 °C
Dry to handle, after	6 - 12 h
Dry to handle, in stack, after	24 h

Note! The shades made from C-base will dry slower.

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Thinner Thinner 1054.

Cleaning of equipment Thinner 1054.

Gloss Matt.

Colours Clear. Limited range of colours according to Valtti Color Card.

PINJASOL COLOR

APPLICATION DETAILS

Application	Stir the oil carefully. The product is ready for use. If needed it can be thinned with Thinner 1054.
Application conditions	The surface to be coated has to be clean and dry. The moisture content of the wood should be below 20 %. During application and drying the temperature of the air, the surface to be treated and the oil has to be over + 5 °C and the relative humidity of the air below 80 %.
VOC	The Volatile Organic Compounds amount is 730 g/litre of oil. Maximum VOC content in ready to use oil is 730 g/l.
HEALTH AND SAFETY	Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oy.

rer130606/snl180108/292-s.