

Temacoat SPA Primer

- DESCRIPTION** A two component resin modified epoxy paint containing anti-corrosive pigments.
- PRODUCT FEATURES AND RECOMMENDED USES**
- ◆ Good adhesion to steel, zinc and aluminium surfaces.
 - ◆ Used as a primer or an intermediate coat on surfaces exposed to climatic, mechanical and chemical stress.
 - ◆ Pigmented with zinc phosphate.
 - ◆ Recommended for building frameworks, tubular bridges, conveyors and other steelwork and equipment.

TECHNICAL DATA

Volume solids 67 ± 2 % (ISO 3233)

Weight solids 80 ± 2 %.

Specific gravity 1.4 kg / l (mixed)

Mixing ratio and product codes

Base	4 parts by volume	008 7240, 7241, 7242
Hardener	1 part by volume	008 5607

Pot life 6 hours (23 °C)

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses		Theoretical coverage
dry	wet	
80 µm	120 µm	8.4 m ² /l
150 µm	225 µm	4.4 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying times

DFT 100 µm	0 °C	+ 10 °C	+ 23 °C	+ 35 °C
Dust dry, after	16 h	4 h	2 h	1 h
Touch dry, after	24 h	10 h	4 h	2 h
Recoatible, min. after	24 h	3 h	1 h	½ h
Recoatible, surfaces to be submerged, min. after	4 d	28 h	12 h	6 h
Recoatible with polyurethane paints, min. after	1 d	5 h	2 h	1 h

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Finish Semimatt.

Colours Reddish brown (TVT 4000) and grey (TVT 4001, 4002).

Temacoat SPA Primer

APPLICATION DETAILS

Surface preparation	<p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p><u>Steel surfaces:</u> Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.</p> <p><u>Zinc surfaces:</u> Sweep blast-clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with PANSSARIPESU detergent.</p> <p>Hot dip galvanized surfaces are recommended to be painted with a mist coat (paint thinned 25 - 30 %) before the actual priming.</p> <p><u>Aluminium surfaces:</u> Sweep blast-clean with non-metallic abrasives to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with MAALIPESU detergent.</p> <p><u>Primed surfaces:</u> Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat. Note the overcoating time of primer. (ISO 12944-4)</p>
Primer	Temacoat SPA Primer, Temazinc 77, Temazinc 88 and Temazinc 99.
Finish	Temacoat HB 30, Temacoat GPL, Temacoat GS 50, Temacoat GPL-S MIO, Temacoat SPA 50, Temadur and Temathane.
Application conditions	<p>All surfaces must be clean and dry and free from contamination. The temperature of the substrate should be minimum +0°C and at least 3°C above the dew point of the air. The product should not be applied at temperatures below 0°C where there is a possibility of ice formation on the substrate.</p> <p>The temperature of paint itself should be above + 15°C for proper application. Good ventilation is required in confined areas during application and drying.</p> <p>Note! There is a natural tendency of epoxy coatings to chalk and discolor on exterior exposure</p>
Mixing components	First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use Temaspeed Squirrel Mixer for mixing.
Application	<p>By airless spray or brush. At spray application the paint should be thinned 0 - 10% by volume. Airless spray nozzle tip 0.015" - 0.021" and nozzle pressure 120 - 180 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>At brush application the paint should be thinned according to the circumstances.</p>
Thinner	Thinner 1031.
Cleaning of equipment	Thinner 1031.
VOC	<p>The Volatile Organic Compounds amount is 310 g/litre of paint mixture. VOC content of the paint mixture (thinned 30 % by volume) is 430 g/l. Only for industrial and professional use.</p>
HEALTH AND SAFETY	<p>Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.</p> <p>A health and safety data sheet is available on request from Tikkurila Oyj.</p>